

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Original) Interference pigments based on coated flake-form substrates, characterised in that they comprise
 - (A) a layer of SiO₂ having a layer thickness of 5-350 nm,
 - (B) a high-refractive-index coating having a refractive index n of > 1.8and/or
 - (C) an interference system consisting of alternating high- and low-refractive-index layersand optionally
 - (D) an outer protective layer.
2. (Original) Interference pigments according to Claim 1, characterised in that the flake-form substrates are natural and/or synthetic mica, talc, kaolin, flake-form iron or aluminium oxides, glass flakes, SiO₂ flakes, TiO₂ flakes, graphite flakes, synthetic support-free flakes, titanium nitride, titanium silicide, liquid crystal polymers (LCPs), holographic pigments, BiOCl or flake-form mixed oxides, or mixtures thereof.
3. (Original) Interference pigments according to Claim 2, characterised in that the flake-form substrates are glass flakes, mica flakes or aluminium oxide flakes.
4. (Currently Amended) Interference pigments according to claim 1 ~~one of Claims 1 to 3~~, characterised in that the thickness of layer (A) is 30-100 nm.

5. (Currently Amended) Interference pigments according to claim 1 ~~one of Claims 1 to 4~~, characterised in that layer (A) is doped with carbon black particles, metal particles and/or coloured pigments.
6. (Currently Amended) Interference pigments according to claim 1 ~~one of Claims 1 to 5~~, characterised in that layer (B) consists of metal oxides.
7. (Original) Interference pigments according to Claim 6, characterised in that the metal oxides are TiO_2 , ZrO_2 , SnO_2 , ZnO , Ce_2O_3 , Fe_2O_3 , Fe_3O_4 , Cr_2O_3 , CoO , Co_3O_4 , VO_2 , V_2O_3 , NiO , titanium suboxides, or mixtures thereof.
8. (Currently Amended) Interference pigments according to Claim 6 ~~or 7~~, characterised in that layer (B) is titanium dioxide.
9. (Currently Amended) Interference pigments according to claim 1 ~~one of Claims 1 to 8~~, characterised in that layer (C) consists of alternating high- and low-refractive-index layers.
10. (Original) Interference pigments according to Claim 9, characterised in that layer (C) has a TiO_2 - SiO_2 - TiO_2 layer sequence.
11. (Currently Amended) Interference pigments according to claim 1 ~~one of Claims 1 to 10~~, characterised in that they have an outer protective layer (D) in order to increase the light, temperature and weather stability.
12. (Original) Process for the preparation of the interference pigments according to Claim 1, characterised in that the coating of the substrates is carried out by wet-chemical methods by hydrolytic decomposition of metal salts in aqueous medium or by gas-phase coating in a fluidised-bed reactor.
13. (Original) Use of the interference pigments according to Claim 1 in paints, coatings, automotive paints, powder coatings, printing inks, security printing inks, plastics, ceramic materials, glasses, paper, in toners for electrophotographic printing processes, in seed, in greenhouse sheeting and tent awnings, as absorbers in the laser marking of paper and plastics, in cosmetic formulations, for the preparation of pigment pastes with water,

organic and/or aqueous solvents, and for the preparation of pigment preparations and dry preparations.